

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
30 October 2003 (30.10.2003)

PCT

(10) International Publication Number
WO 03/089023 A1(51) International Patent Classification⁷: **A61L 27/30,**
A61F 2/30MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/GB03/01264

(22) International Filing Date: 25 March 2003 (25.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).(30) Priority Data:
0208642.9 16 April 2002 (16.04.2002) GB(71) Applicant (*for all designated States except US*): ACCEN-
TUS PLC [GB/GB]; 329 Harwell, Didcot, Oxfordshire
OX11 0QJ (GB).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): PICKFORD,
Martin, Edward, Lee [GB/GB]; 37 Downland Close,
Locks Heath, Southampton, Hampshire SO31 6WB (GB).
TURNER, Andrew, Derek [GB/GB]; 17 Loyd Close,
Abingdon, Oxfordshire OX14 1SR (GB).(74) Agents: MANSFIELD, Peter, Turquand et al.; Accentus
plc, Patents Dept, 329 Harwell, Didcot, Oxfordshire OX11
0QJ (GB).(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)*
- *of inventorship (Rule 4.17(iv)) for US only*

Published:

- *with international search report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METAL IMPLANTS

(57) Abstract: A metal implant for use in a surgical procedure is provided with a surface layer that is integral with the metal substrate, and which incorporates a biocidal material. The surface layer may be grown from the metal substrate, by anodising, and the biocidal material incorporated in it by ion exchange. Alternatively the layer may be deposited by electroplating, followed by diffusion bonding so as to become integral with the metal substrate. In either case, silver is a suitable biocidal material; and both the release rate and the quantity of biocidal material should be low to avoid toxic effects on body cells. Electropolishing the surface before formation of the surface layer is also beneficial, and this may be achieved by electropolishing.

WO 03/089023 A1